

TECHNICAL DATA

(ANTISLIP TAPES)

Subject	Result	Test Method
Back Carrier	0.1mm Thick Film	Calliper method
Type of adhesive	Solvent Acrylic	N/A
Adhesion (G/In)	0.37 +/- 0.02	PSTC-4
Tensile (KGs/Ins)	6.5 +/- 0.5	PSTC-31
Tear Resistance (G)	5600 +/- 200	PSTC-39
Elongation at break (%)	110 +/- 15	PSTC-31
Temperature Range (C)	-30 to +70 deg.C	see notes below
Max of log roll	40" * 50 yds	N/A
Resistance to water (months)	10	PSTC-35
Resistance to Chemicals (months)	8	PSTC-35
Resistance to Motor Oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

GLOW in the Dark tape results:

30 millicandela per m² at 2 minutes, 5mcd after 10 minutes

Coefficient of friction and comparison of various surfaces:

Non-Slip surface	Dry surface test result	Wet surface test result
Coarse	1.33	1.21
Standard	1.29	1.09
Fine	1.37	1.17

Other surfaces		
Ribbed rubber	0.89	0.76
Standerd nonslip paint	0.69	0.50
Painted steel	0.77	0.69
Textured vinyl	0.80	0.64
Ribbed vinyl	0.85	0.72